



| | |
|------------------------|---------------------------|
| Product Code | 440070 |
| Product Name | BONDEX Decking Oil |
| Recommended for | Wooden decks - Exterior |
| Available sizes | 2.50 L - 5.00 L - 20.00 L |

1 Product Description

| | | |
|-----|--------------------|--|
| 1.1 | Product Type: | Special oil for the care of wooden decks and terraces. |
| 1.2 | Manufacturer: | Dyrup A/S - Gladsaxevej 300 - 2860 Søborg - Denmark Phone: +45 39 57 93 00 - www.bondexwood.com |
| 1.3 | Where to use: | For treatment and maintenance of all exterior wooden decks and terraces. |
| 1.4 | Special Qualities: | Hard wearing. The oil gives a water repellent effect. The original glow of the wood is preserved. Protection against the weather. |
| 1.5 | Form Supplied: | Ready to use. |

2 Composition

| | | |
|-----|--------------|----------------------------------|
| 2.1 | Binder: | Alkyd. |
| 2.2 | Solvents: | White spirit. |
| 2.3 | VOC-content: | Not regulated by VOC-regulation. |
| 2.4 | Pigments: | Organic and inorganic pigments. |

3 Technical Data

| | | |
|-----|-------------------|---|
| 3.1 | Specific gravity: | App. 0.9 kg/l. |
| 3.2 | Viscosity: | >62 sec./ISO cup 6 mm/23 ⁰ . |
| 3.3 | Flash point: | App. 62 ⁰ C, Pensky Martens. |
| 3.4 | Gloss: | Matt. |



| | | |
|------|---------------------|---|
| 3.5 | Solid content: | App. 51 W/W% / 45,5 v/v%. |
| 3.6 | Odour: | Strong. |
| 3.7 | Coverage | 10-16 m ² /l, depending on the type of wood and the state of substrate. |
| 3.8 | Drying time: | <u>Touch dry</u> : 3-5 hours. <u>Recoatable</u> : App. 24 hours. Measured at 23 ⁰ C and standard humidity of 60%. Terraces can be used 48 hours after application. <u>Through hardening</u> : App. 1 week. |
| 3.9 | Weather resistance: | Water repellent. |
| 3.10 | Fungicide: | Yes. |
| 3.11 | Thinning: | Do not thin. |
| 3.12 | Storage: | Store frost free. |
| 3.13 | Shelf life: | 3 years in unopened container. |

4 Surface and preparation

| | | |
|-----|---------------------------------|---|
| 4.1 | In general: | Stir well before use. |
| 4.2 | Substrate: | The surface must be clean, dry and solid. |
| 4.3 | Humidity / Moisture content: | The wood moisture at the time of treatment must not exceed 18%. |

5 Treatment

| | | |
|-----|---------------------|---|
| 5.1 | Application method: | Apply by brush until the wood is saturated. Remove excess oil with a lint free cloth. |
| 5.2 | Pre-treatment: | Previously treated surfaces should be cleaned with BONDIX Deck Cleaner. Rinse with clean water. Decayed wood must be planed down to sound wood. |
| 5.3 | Treatment: | 2 x BONDIX Decking Oil. |
| 5.4 | Cleaning of tools | Clean tools immediately in white spirit. |

6 Safety precautions

| | | |
|-----|-------------|--|
| 6.1 | In general: | Common safety rules for work with paints and varnishes must be observed. |
|-----|-------------|--|



6.2 Safety instructions: Further information is available from our Material Safety Data Sheet.

7 Disposal

7.1 Disposal: Do not empty into drains or into the environment. Product waste must not be poured into the sewers, water reserves or soil. Left over product should be handed in at your local waste disposal. Empty can may be recycled (check with your local waste disposal site or your local authorities).

The purpose of this Technical Data Sheet is to provide our clients with information about the properties and characteristics of the product. The information provided is based on tests conducted by us under usage conditions that comply with the prevailing standards. Our recommendations for use are for information only, and in no event shall they take precedence over any specific recommendation taking into account the nature and conditions of a particular site, nor shall they engage PPG's liability. Before all applications of the product, clients should check that this document has not been amended by a more recent version, which takes into account new technical data. This version annuls and replaces all previous versions of Technical Data Sheets relating to this product.
